



GRANOWSKI STEEL SHOT ABRASIVE

PHYSICAL SPECIFICATIONS


Specific Density: 7.4 – 7.6 gm/cc
Bulk Density: 4.3 – 4.7 gm/cc
Hardness HRC: 40 – 50

For more information on Granowski Steel Shot Abrasive, visit:
<http://www.granowski.com.au/Abrasives/Steel-Shot-Abrasive.aspx>

STEEL SHOT CHART

Product	7	8	10	12	14	16	18	20	25	30	35	40	45	50	80	120	200	Average No. Pellets / Kg.
S780	▼		85% min	97% min														24,200
S660		▼		85% min	97% min													41,800
S550			▼		85% min	97% min												66,000
S460			▼	5% max		85% min	96% min											121,000
S390				▼	5% max		85% min	96% min										198,000
S330					▼	5% max		85% min	96% min									330,000
S280						▼	5% max		85% min	96% min								550,000
S230							▼	10% max		85% min	97% min							1,052,500
S170								▼	10% max			85% min	97% min					2,200,000
S110										▼	10% max			80% min	90% min			6,600,000
Screen Number	7	8	10	12	14	16	18	20	25	30	35	40	45	50	80	120	200	
Screen Size mm	2.83	2.38	2.00	1.70	1.40	1.18	1.00	0.84	0.71	0.60	0.50	0.425	0.355	0.30	0.180	0.125	0.075	
Screen Size inches	0.111	0.0937	0.0787	0.0661	0.0555	0.0459	0.0394	0.0331	0.0280	0.0232	0.0197	0.0165	0.0136	0.0117	0.007	0.0049	0.0029	

STEEL SHOT SAMPLE



Since 1982 – Australian Designers, Manufacturers & Suppliers of:

Air & Airless Blast Cleaning and Peening Equipment Component Cleaning & Degreasing Systems
Full Range of Quality Abrasives Spare Parts, Service and Support